

# 亜鉛フレーク粉 Zn-S-D8S

Flake Zinc Powder

## ■ 特長 Advantages

ドライタイプでアスペクト比が高いフレーク状の亜鉛粉末

Dry Type, High Aspect Ratio Flake Zinc Powder

## ■ 粉末特性 Properties

50%平均粒径 ( $\mu\text{m}$ ) : 7.0 ~ 12.0

Median Diameter

見掛密度 ( $\text{g}/\text{cm}^3$ ) : 1.0 ~ 1.9

Apparent Density

比表面積 ( $\text{m}^2/\text{g}$ ) : 0.8 ~ 1.4


Specific Surface Area

\* 記載は全て代表値であり、保証値ではありません。また、事前の予告なく変更されることがあります。

\*All figures shown above are typical values and are not guaranteed.

Properties may be changed without advanced notice.

SEM写真×2000



 **FUKUDA** 福田金属箔粉工業株式会社 FUKUDA METAL FOIL & POWDER CO.,LTD.

本社 〒607-8305 京都市山科区西野山中臣町20番地

東京支店 〒103-0027 東京都中央区日本橋3丁目9番1号(日本橋三丁目スクエア12階)

名古屋支店 〒460-0003 名古屋市中区3丁目7番9号(太陽生命名古屋第二ビル3階)

関西支店 〒600-8435 京都市下京区松原通室町西入中野之町172番地

<https://www.fukuda-kyoto.co.jp/>

Phone 075-581-2161 FAX 075-581-7271 20 Nakatomi-cho, Nishinoyama, Yamashina-ku, Kyoto 607-8305, Japan

Phone 03-4574-6777 FAX 03-4574-6768 12th Floor, NIHOMBASHI 3-CHOME SQUARE, 3-9-1 Nihombashi, Chuo-ku, Tokyo, 103-0027, Japan

Phone 052-961-7851 FAX 052-961-0102 3rd Floor, Taiyo-Seimei Nagoya Bldg. 2, 3-7-9 Nishiki, Naka-ku, Nagoya 460-0003, Japan

Phone 075-361-2314 FAX 052-361-2309 172 Nakanono-cho, Matsubara-dori Muromachi Nishiiru, Shimogyo-ku, Kyoto 600-8435, Japan

2025/10

© 2014-2025 FUKUDA METAL FOIL & POWDER CO., LTD. All Rights Reserved.